

INTERNATIONAL STANDARD

ISO
14125

First edition
1998-03-01

AMENDMENT 1
2011-02-01

Fibre-reinforced plastic composites — Determination of flexural properties

AMENDMENT 1

*Composites plastiques renforcés de fibres — Détermination
des propriétés de flexion*

AMENDMENT 1

STANDARDSISO.COM : Click to view the full PDF of ISO 14125:1998/Amd.1:2011



Reference number
ISO 14125:1998/Amd.1:2011(E)

© ISO 2011

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 14125:1998 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 13, *Composites and reinforcement fibres*.

STANDARDSISO.COM : Click to view the full PDF of ISO 14125:1998/Amd 1:2011

Fibre-reinforced plastic composites — Determination of flexural properties

AMENDMENT 1

Page 2

Replace Clause 2, "Normative references", by the following clause, in which the introductory paragraph and references have been updated:

2 Normative references

The following referenced documents are essential indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 178, *Plastics — Determination of flexural properties*

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 293, *Plastics — Compression moulding of test specimens of thermoplastic materials*

ISO 294-1, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 1: General principles, and moulding of multipurpose and bar test specimens*

ISO 295, *Plastics — Compression moulding of test specimens of thermosetting materials*

ISO 1268 (all parts), *Fibre-reinforced plastics — Methods of producing test plates*

ISO 2602, *Statistical interpretation of test results — Estimation of the mean — Confidence interval*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 3167, *Plastics — Multipurpose test specimens*

ISO 5893, *Rubber and plastics test equipment — Tensile, flexural and compression types (constant rate of traverse) — Specification*

Page 4, Definition 4.9

Insert the following as a second paragraph:

With materials which have a failure strain of less than 0,002 5 (e.g. high-modulus carbon-fibre-reinforced plastics), the strain difference used to calculate the flexural modulus is reduced to 0,001 0 – 0,000 5.

Page 10, Subclause 10.1.2, and page 11, Subclause 10.2.2

Replace the first two lines in each subclause by the following:

For the measurement of the flexural modulus, calculate the deflections s' and s'' which correspond to the given values of flexural strain $\varepsilon_f' = 0,000\ 5$ and $\varepsilon_f'' = 0,002\ 5$ in the case of composites with a failure strain greater than 0,002 5 or calculate the deflections s' and s'' which correspond to the given values of flexural strain $\varepsilon_f' = 0,000\ 5$ and $\varepsilon_f'' = 0,001\ 0$ in the case of materials, such as high-modulus carbon-fibre-reinforced plastics, which have a failure strain of less than 0,002 5, using the following equation:

Page 13, Clause 12

Replace the text of item n) by the following:

the equation and the strain range (i.e. strain difference) used;

STANDARDSISO.COM : Click to view the full PDF of ISO 14125:1998/Amd 1:2011