



400 COMMONWEALTH DRIVE, WARRENTALE, PA 15096

AEROSPACE MATERIAL SPECIFICATION

AMS 3792/2A

Issued 10-1-83
Revised 1-1-89

Superseding AMS 3792/2

Submitted for recognition as an American National Standard

TAPE, LOW MODULUS ARAMID 2 (51), 1000 (4448) Breaking Strength

1. SCOPE:

1.1 Form: This specification covers one weight of low-modulus aramid tape.

1.2 Application: Primarily for use in construction of parachutes.

1.3 Classification: 2.0 inches (51 mm) wide low-modulus aramid tape having 1000 pounds force (4448 N) breaking strength.

2. APPLICABLE DOCUMENTS: See AMS 3792.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for procuring the tape described herein shall consist of this document and the latest issue of the basic specification, AMS 3792.

3.2 Construction and Properties:

3.2.1 Yarn:

3.2.1.1 Denier and Filament Count: The yarn shall be 200 denier \pm 15 and shall consist of 100 filaments \pm 10.

3.2.1.2 Ply: The warp yarns shall be 1 ply. The filling yarns shall be 2 ply.

3.2.1.3 Twist: The warp yarns shall be twisted 5.0 ± 1 turns per inch (25.4 mm). The filling yarns shall be twisted 3.0 ± 1 turns per inch (25.4 mm).

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.