

**AEROSPACE
MATERIAL
SPECIFICATION****AMS 5604E**

| | |
|-----------------------|----------|
| Issued | MAY 1968 |
| Revised | NOV 2001 |
| Reaffirmed | OCT 2006 |
| Superseding AMS 5604D | |

Steel, Corrosion Resistant, Sheet, Strip, and Plate

16.5Cr - 4.0Ni - 4.0Cu - 0.30Cb

Solution Heat Treated, Precipitation Hardenable

(Composition similar to UNS S17400)

RATIONALE

This document has been reaffirmed to comply with the SAE 5-year Review policy.

1. SCOPE:**1.1 Form:**

This specification covers a corrosion-resistant steel in the form of sheet, strip, and plate.

1.2 Application:

These products have been used typically for parts requiring corrosion resistance and high strength up to 600 °F (316 °C) and where such parts may require welding during fabrication, but usage is not limited to such applications.

1.2.1 Certain processing procedures and service conditions may cause these products to become subject to stress-corrosion cracking; ARP1110 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)

Fax: 724-776-0790

Email: CustomerService@sae.org

SAE WEB ADDRESS: <http://www.sae.org>

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

| | |
|----------|---|
| AMS 2242 | Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate |
| MAM 2242 | Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate |
| AMS 2248 | Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys |
| AMS 2315 | Determination of Delta Ferrite Content |
| AMS 2371 | Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock |
| AMS 2750 | Pyrometry |
| AMS 2807 | Identification, Carbon and Low-Alloy Steels, Corrosion and Heat Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing |
| AS4194 | Sheet and Strip Surface Finish Nomenclature |
| ARP1110 | Minimizing Stress-Corrosion Cracking in Wrought Forms of Steels and Corrosion Resistant Steels and Alloys |

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or www.astm.org.

| | |
|-------------------|---|
| ASTM A 480/A 480M | Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip |
| ASTM A 370 | Mechanical Testing of Steel Products |
| ASTM E 353 | Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys |

3. TECHNICAL REQUIREMENTS:**3.1 Composition:**

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

| Element | min | max |
|------------|-------|-------|
| Carbon | -- | 0.07 |
| Manganese | -- | 1.00 |
| Silicon | -- | 1.00 |
| Phosphorus | -- | 0.040 |
| Sulfur | -- | 0.030 |
| Chromium | 15.00 | 17.50 |
| Nickel | 3.00 | 5.00 |
| Columbium | 5xC | 0.45 |
| Copper | 3.00 | 5.00 |
| Molybdenum | -- | 0.50 |

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2248.

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Sheet and Strip: Cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance in accordance with ASTM A 480/A 480M and AS4194 comparable to a No. 2D finish.

3.2.2 Plate: Hot rolled, solution heat treated, and descaled.

3.3 Solution Heat Treatment:

The product shall be solution heat treated by heating to $1900^{\circ}\text{F} \pm 25$ ($1038^{\circ}\text{C} \pm 14$), holding at heat for a time commensurate with the thickness and the heating equipment and procedure used, and cooling to below 90°F (32°C). Pyrometry shall conform to AMS 2750.

3.4 Properties:

The product shall conform to the following requirements; tensile, hardness, and bend testing shall be performed in accordance with ASTM A 370:

3.4.1 As Solution Heat Treated:

3.4.1.1 Tensile Properties: Shall be as shown in Table 2 for nominal thickness 0.015 to 0.1874 inch (0.38 to 4.760 mm), inclusive.

TABLE 2 - Solution Treated Tensile Properties

| Property | Value |
|---------------------------------------|--------------------|
| Tensile Strength, max | 185 ksi (1276 MPa) |
| Yield Strength at 0.2% Offset, max | 160 ksi (1103 MPa) |
| Elongation in 2 Inches (50.8 mm), min | 3% |

3.4.1.2 Hardness: Shall be not higher than 38 HRC, or equivalent (See 8.2).

3.4.1.3 Microstructure: The product shall contain not more than 5% ferrite, determined in accordance with AMS 2315.

3.4.1.4 Bending: Product 0.109 inch (2.77 mm) and under in nominal thickness shall withstand, without cracking, bending through an angle of 180 degrees around a diameter equal to 18 times the nominal thickness of the product, with axis of bend parallel to the direction of rolling.

3.4.2 After Precipitation Heat Treatment: The solution heat treated product 4.0 inches (102 mm) and under in nominal thickness shall have tensile properties specified in 3.4.2.1 and hardness specified in 3.4.2.2 after being precipitation heat treated to a particular condition in accordance with the corresponding temperature and times shown in Table 3 and cooled as required. Tensile and hardness tests shall be made in only the H900 condition unless purchaser specifies another heat treated condition.

TABLE 3 - Precipitation Hardening Conditions

| Condition | Temperature | Time |
|-----------|---------------------------|----------------|
| H900 | 900 °F ± 10 (482 °C ± 6) | 60 minutes ± 5 |
| H925 | 925 °F ± 10 (496 °C ± 6) | 4 hours ± 0.25 |
| H1025 | 1025 °F ± 10 (552 °C ± 6) | 4 hours ± 0.25 |
| H1075 | 1075 °F ± 10 (579 °C ± 6) | 4 hours ± 0.25 |
| H1100 | 1100 °F ± 10 (593 °C ± 6) | 4 hours ± 0.25 |
| H1150 | 1150 °F ± 10 (621 °C ± 6) | 4 hours ± 0.25 |

3.4.2.1 Tensile Properties: Shall be as shown in Table 4.

TABLE 4A - Minimum Tensile Properties After Precipitation Heat Treatment, Inch/Pound Units

| Condition | Nominal Thickness Inches | | Tensile Strength ksi | Yield Strength at 0.2% Offset ksi | Elongation in 2 Inches or 4D % | Reduction of Area % |
|-----------|-----------------------------|--|-------------------------|---|---|---------------------------|
| H900 | Up to 0.1874, incl | | 190 | 170 | 5 | -- |
| | 0.1875 to 0.625, incl | | 190 | 170 | 8 | 30 |
| | Over 0.625 to 4.000, incl | | 190 | 170 | 10 | 35 |
| H925 | Up to 0.1874, incl | | 170 | 155 | 5 | -- |
| | 0.1875 to 0.625, incl | | 170 | 155 | 8 | 30 |
| | Over 0.625 to 4.000, incl | | 170 | 155 | 10 | 35 |
| H1025 | Up to 0.1874, incl | | 155 | 145 | 5 | -- |
| | 0.1875 to 0.625, incl | | 155 | 145 | 8 | 35 |
| | Over 0.625 to 4.000, incl | | 155 | 145 | 12 | 40 |
| H1075 | Up to 0.1874, incl | | 145 | 125 | 5 | -- |
| | 0.1875 to 0.625, incl | | 145 | 125 | 9 | 35 |
| | Over 0.625 to 4.000, incl | | 145 | 125 | 13 | 45 |
| H1100 | Up to 0.1874, incl | | 140 | 115 | 5 | -- |
| | 0.1875 to 0.625, incl | | 140 | 115 | 10 | 35 |
| | Over 0.625 to 4.000, incl | | 140 | 115 | 14 | 45 |
| H1150 | Up to 0.1874, incl | | 135 | 105 | 8 | -- |
| | 0.1875 to 0.625, incl | | 135 | 105 | 10 | 40 |
| | Over 0.625 to 4.000, incl | | 135 | 105 | 16 | 50 |

TABLE 4B - Minimum Tensile Properties After Precipitation Heat Treatment, SI Units

| Condition | Nominal Thickness Millimeters | | | Tensile Strength MPa | Yield Strength at 0.2% Offset MPa | Elongation in 50.8 mm or 4D % | Reduction of Area % |
|-----------|----------------------------------|------|------|-------------------------|---|--|---------------------------|
| H900 | Up to 4.760, incl | 1310 | 1172 | 5 | -- | 8 | 30 |
| | 4.761 to 15.88, incl | 1310 | 1172 | 8 | -- | | |
| | Over 15.88 to 101.60, incl | 1310 | 1172 | 10 | 35 | | |
| H925 | Up to 4.760, incl | 1172 | 1069 | 5 | -- | 8 | 30 |
| | 4.761 to 15.88, incl | 1172 | 1069 | 8 | -- | | |
| | Over 15.88 to 101.60, incl | 1172 | 1069 | 10 | 35 | | |
| H1025 | Up to 4.760, incl | 1069 | 1000 | 5 | -- | 8 | 35 |
| | 4.761 to 15.88, incl | 1069 | 1000 | 8 | -- | | |
| | Over 15.88 to 101.60, incl | 1069 | 1000 | 12 | 40 | | |
| H1075 | Up to 4.760, incl | 1000 | 862 | 5 | -- | 9 | 35 |
| | 4.761 to 15.88, incl | 1000 | 862 | 9 | -- | | |
| | Over 15.88 to 101.60, incl | 1000 | 862 | 13 | 45 | | |
| H1100 | Up to 4.760, incl | 965 | 793 | 5 | -- | 10 | 35 |
| | 4.761 to 15.88, incl | 965 | 793 | 10 | -- | | |
| | Over 15.88 to 101.60, incl | 965 | 793 | 14 | 45 | | |
| H1150 | Up to 4.760, incl | 931 | 724 | 8 | -- | 10 | 40 |
| | 4.761 to 15.88, incl | 931 | 724 | 10 | -- | | |
| | Over 15.88 to 101.60, incl | 931 | 724 | 16 | 50 | | |

3.4.2.2 Hardness: Shall be within the range shown in Table 5 for the corresponding precipitation heat treatment condition.

TABLE 5 - Hardness

| Condition | HB | HRC | HV |
|-----------|------------|----------|------------|
| H900 | 375 to 444 | 40 to 47 | 411 to 510 |
| H925 | 352 to 415 | 38 to 45 | 392 to 473 |
| H1025 | 331 to 388 | 35 to 42 | 364 to 431 |
| H1075 | 311 to 363 | 33 to 39 | 344 to 401 |
| H1100 | 302 to 352 | 32 to 38 | 333 to 392 |
| H1150 | 269 to 341 | 28 to 37 | 280 to 383 |